



**Bearings** | **Technical Data**

**More Info**

**Shaft Requirements**

BEARING MEDIUM	SHAFT REQUIREMENTS	
	Hardness	Surface Finish
Teflon-Bronze	Hard or Soft	16 RMS Min.
SAE 840 Bronze	Min. hardness of 95 HRB (Rockwell B)	16 RMS Min.
Delrin	Hard or Soft	16 RMS Min.
Needle-Roller	Hardness of 58-64 HRC (Rockwell C)	16 RMS Min.

- [Mounting Options](#)
- [Coefficient of Friction](#)
- [Material Content & Structure](#)
- [Operating Temperature](#)
- [Shaft Requirements](#)
- [Maintenance](#)
- [Storage](#)
- [PV Values](#)
- [Wear/Life Calculation](#)